

Technical Datasheet - METYX Composite Reinforcements

| PRODUCT CODE | 5200.000.010 | | |
|---------------------|---------------------------------|--|--|
| PRODUCT NAME | METYCORE-450M/180PP1/450M-127CM | | |
| PRODUCT DESCRIPTION | RTM FABRIC | | |
| CUSTOMER CODE | | | |
| CUSTOMER ID | | | |

| REINFORCEMENT CONSTRUCTION | | | | |
|----------------------------|--------|------------|-------------|--|
| | LAYER | FIBER TYPE | AREA WEIGHT | |
| 1 | CSM | 2400 Tex | 450 gr / m2 | |
| 2 | NW | РР | 180 gr / m2 | |
| 3 | CSM | 2400 Tex | 450 gr / m2 | |
| 4 | Stitch | 76 Dtex | 7 gr / m2 | |
| 5 | | | | |
| 6 | | | | |
| 7 | | | | |

^{*} Checked via own test based on ISO 3374.

TOTAL* 1087 gr / m2 (± %10)

| OTHER PROPERTIES | | | ROLL INFO | |
|-----------------------|-----------------|---------------|-----------|--|
| Stitch Gauge | 3 stitches/inch | Roll Width | 127 cm | |
| Stitch Type | Tricot | Roll Weight | 81 kg | |
| Stitch Length | 4 mm | Roll Length | 55 m | |
| Pilot Yarn / Position | / | Core Diameter | 76 mm | |

| Resin Compatibility | Loss on Ignition | Moisture Content |
|-------------------------------------|--------------------------------|--------------------------------|
| Polyester, Vinylester, Epoxy resins | Max.%0,55 by weight (ISO 1887) | Max.%0,20 by weight (ISO 3344) |

| Packaging | All rolls are wrapped with polyethylene bags; placed in pallet boxes or in single cardboard boxes or in pyramid style on pallets. | |
|--|---|--|
| Labelling Each roll is labelled on the inner side of the core, on the bag or on the cardboa including a unique reference number for its traceability. | | |
| Storage | Store at %40-70 relative humidity and 18-30 °C temperature range. Recommended to be brought to working area 24 hrs prior to use. | |

| Certification | DNV | Lloyd's Register |
|---|-----|------------------|
| Metyx products are produced by Telateks A.S. company who is run by ISO 9001:2008 QA System. | - | |

Note: The above specifications reflect the product data on release date but are subject to change without prior notice.

Address:

Orhanli Beldesi 34956 Tuzla Istanbul – TURKIYE



Phone: +90-216-394-32-60
Fax: +90-216-394-32-58
Web: www.metyx.com

TDM-İ.00/20.03.08 FR-4.01-12B.00