

## **Technical Datasheet - METYX Composite Reinforcements**

PRODUCT CODE	5200.000.187	
PRODUCT NAME	METYCORE-300M/125PP1/300M-127CM	
PRODUCT DESCRIPTION		
CUSTOMER CODE	•	
CUSTOMER ID	•	

REINFORCEMENT CONSTRUCTION			
	LAYER	FIBER TYPE	AREA WEIGHT
1	CSM	2400 Tex	300 gr / m2
2	Core	PP	125 gr / m2
3	CSM	2400 Tex	300 gr / m2
4	Stitch	76 Dtex	7 gr / m2
5			
6			
7			

<sup>\*</sup> Checked via own test based on ISO 3374.

TOTAL*	732 gr / m2	<b>2</b> (± %10)
--------	-------------	------------------

OTHER PROPERTIES		R	ROLL INFO	
Stitch Gauge	3 stitches/inch	Roll Width	163 cm	
Stitch Type	Tricot	Roll Weight	60 kg	
Stitch Length	3 mm	Roll Length	65 m	
Pilot Yarn / Position	/	Core Diameter	76 mm	

Resin Compatibility	Loss on Ignition	Moisture Content
Polyester, Vinylester, Epoxy resins	Max.%0,55 by weight (ISO 1887)	Max.%0,20 by weight (ISO 3344)

Packaging	All rolls are wrapped with polyethylene bags; placed in pallet boxes or in single cardboard boxes or in pyramid style on pallets.
Labelling	Each roll is labelled on the inner side of the core, on the bag or on the cardboard boxes including a unique reference number for its traceability.
Storage	Store at %40-70 relative humidity and 18-30 °C temperature range. Recommended to be brought to working area 24 hrs prior to use.

Certification	DNV	Lloyd's Register
Metyx products are produced by Telateks A.S. company		_
who is run by ISO 9001:2008 QA System.	-	-

**Note:** The above specifications reflect the product data on release date but are subject to change without prior notice.

## Address:

Orhanli Beldesi 34956 Tuzla Istanbul – TURKIYE



Phone: +90-216-394-32-60
Fax: +90-216-394-32-58
Web: www.metyx.com

TDM- .00/20.03.08 TELATEKS TEKSTIL URUNLER SANAYI VY TICARET A.S. FR-4.01-12B.00